

### **LISTING OF THE CLAIMS**

The status of the claims is as follows.

1. (Previously presented) A can, comprising:  
a body portion; and  
an end portion,  
wherein at least one of the body and end portions are aluminum and are coated on at least one major surface with a coating composition comprising: a blend of two or more polyester resins each formed by the reaction of one or more polyacid molecules and one or more polyol molecules, wherein the blend has (i) between about 60 and 90 weight percent polyester resin having a  $T_g$  less than about 25°C and (ii) between about 10 and 40 weight percent polyester resin having a  $T_g$  greater than 50°C; and a crosslinker, and  
wherein the coating composition is substantially free of mobile BPA and aromatic glycidyl ether compounds.
2. (Cancelled)
3. (Original) The can of claim 1, wherein the coating composition is essentially completely free of mobile BPA and aromatic glycidyl ether compounds.
4. (Original) The can of claim 1, wherein the coating composition is also substantially free of bound BPA and aromatic glycidyl ether compounds.
5. (Original) The can of claim 1, wherein the coating composition is essentially free of mobile BPA, BADGE, BFDGE and NOGE compounds.
6. (Original) The can of claim 1, wherein the polyol molecules used to make the polyester resin are substantially free of NPG.
- 7-8. (Cancelled)

9. (Previously presented) The can of claim 3, wherein the blend has between about 70 and 90 weight percent polyester resin having a  $T_g$  less than about 25 °C and between about 10 and 30 weight percent polyester resin having a  $T_g$  greater than about 50 °C.
10. (Original) The can of claim 1, wherein the polyester resin has a number average molecular weight between about 5,000 and 20,000 Daltons.
11. (Original) The can of claim 1, wherein the polyester resin has an acid number less than about 5.
12. (Original) The can of claim 1, wherein the polyester resin has an OH number less than about 20.
13. (Original) The can of claim 1, wherein the coating composition comprises between 60 and 95 weight percent polyester resin based on solids content.
14. (Original) The can of claim 1, wherein the coating composition comprises between 65 and 85 weight percent polyester resin based on solids content.
15. (Original) The can of claim 1, wherein the coating composition comprises between 10 and 30 weight percent crosslinker based on solids content.
16. (Original) The can of claim 1, wherein the coating composition further comprises 2 to 10 weight percent acrylate copolymer, based on solids content.
17. (Original) The can of claim 16, wherein the acrylate copolymer comprises one or more glycidyl groups.
18. (Original) The can of claim 1, wherein the end portion is made of aluminum and the coating is applied to the aluminum prior to the end being fabricated.

19. (Original) The can of claim 18, wherein both sides of the end portion are coated with the coating composition.

20. (Previously presented) A method of making a can, comprising the steps of:

forming a can body;

forming a can end;

wherein at least one of the end and the body are coated on at least one side with a coating composition comprising: a blend of two or more polyester resins each formed by the reaction of one or more polyacid molecules and one or more polyol molecules, wherein the blend has (i) between about 60 and 90 weight percent polyester resin having a  $T_g$  less than about 25°C and (ii) between about 10 and 40 weight percent polyester resin having a  $T_g$  greater than 50°C; and a crosslinker, wherein the coating composition is substantially free of mobile BPA and aromatic glycidyl ether compounds;

filling the body with a liquid; and

attaching the end to the body.

21. (Original) The method of claim 20, wherein the coating composition is applied to a metal sheet and cured, and wherein the coated sheet is then formed into at least one of the end and the body.

22-25. (Cancelled)

26. (Previously presented) The can of claim 1, wherein the coating composition comprises from 60 to 95 weight percent (based on the solid content of the composition) of the blend of two or more polyester resins and from 5 to 40 weight percent (based on the solids content of the composition) of crosslinker.

27. (Previously presented) The method of claim 20, wherein the liquid comprises a food or beverage.

28. (Previously presented) The can of claim 1, wherein the crosslinker comprises a phenoplast.
29. (Previously presented) The can of claim of claim 1, wherein the blend of two or more polyester resins includes between about 60 and 90 weight percent polyester resin having a  $T_g$  between 15 and 25°C.
30. (Previously presented) A can, comprising:  
a body portion; and  
an end portion;  
wherein at least one of the body and end portions are coated on at least one major surface with a coating composition comprising:  
a blend of two or more polyester resins, wherein the blend has (i) between about 60 and 90 weight percent polyester resin having a  $T_g$  less than about 25°C and (ii) between about 10 and 40 weight percent polyester resin having a  $T_g$  greater than 50°C,  
an acrylate copolymer having pendant glycidyl groups, and  
a crosslinker;  
wherein the coating composition is substantially free of bound BPA and aromatic glycidyl ether compounds.